



South Down Multi

South Down Multi

Manufactured to BS EN 771-1

Brick type

Category II, HD, Clay Masonry Unit

Standard work size

215 x 102.5 x 65mm

Dimensional tolerances

Tolerance category: T2

Range category: R1

Compressive strength

≥ 75N/mm²

Water absorption

≤ 7%

Durability

F2

Active soluble salts content

S2

Configuration

Vertically perforated 24-29% voids

Dry weight per brick

2.40kg

Pack size

452

Factory

Howley Park

DISCLAIMER:

The reproduction of colours and textures is only as accurate as the printing process will allow. Photographic samples should be used when shortlisting products but we advise that an actual sample should be seen before ordering.

This panel is printed on paper made using ecf from fibres obtained from a sustainable timber source.



BES 6001

Responsible Sourcing

www.greenbooklive.com



Hanson Building Products
222 Peterborough Road
Whittlesey
Cambridgeshire
PE7 1PD

Sales: 0330 123 1017

Technical: 0330 123 1018

Fax: 01733 206040

www.hanson.com/uk

[twitter@Hanson_UK](https://twitter.com/Hanson_UK)